




42 ALLOY



CHEMICAL COMPOSITION %	
Chemical Element	42 Alloy
Iron	Bal
Nickel	41
Manganese	0.80
Silicon	0.30
Carbon	0.05
Aluminum	0.10
Chromium	0.25
Phosphorus	0.025
Sulfur	0.025
PHYSICAL PROPERTIES	
Property	42 Alloy
Density	0.293
Specific Gravity	8.12
Specific Heat	0.12
Curie Temperature	716
Melting Point	2600
Electrical Resistivity	430
Thermal Conductivity	74.5
Linear coefficient of thermal expansion cm. per cm. per °C x 10 ⁻⁶	
Temp. range – °C	42 Alloy
30-300	4.0 - 4.7

Certified to ASTM F30,
AMS/MIL I 23011 Class 5

42 Alloy, a low expansion alloy, is very similar to Invar 36 with a slightly different Coefficient of Thermal Expansion. This nickel-iron alloy is ideal for lid, lead frames, stencil/etching, telecommunications and aircraft industry, offering a more affordable alternative to Kovar when a tight seal is not required.

42 Alloy has a virtually constant low rate of thermal expansion at temperatures up to approximately 650°F (343°C). Easily machined and formed hot or cold, 42 Alloy is also used extensively in the medical, electronics and automotive industries.

Let National Electronic Alloys help you analyze your business needs and objectives. Our procurement side and supply side experience can save you money and ensure that you make the best possible purchasing decisions.

NEA ISO 9001 Certified
Specialty Metal Service Center
Dedicated to Customer Service & Quality

NATIONAL ELECTRONIC ALLOYS
www.nealloys.com

EAST COAST

3 Fir Court, Oakland, NJ 07436
201-337-9400 • Fax: 201-337-9698
Toll Free: 800-524-4309
Email: Sales@nealloys.com

WEST COAST

1847 W. Business Center Dr., Orange, CA 92867
714-556-5561 • Fax: 714-556-5562
Toll Free: 877-632-9378
Email: Sales@nealloyswest.com

42 ALLOY FROM STOCK

42 Alloy Plate

Thick.	Width	Length	Thick.	Width	Length
.157"	x 16.5"	x 72"	.450"	x 16.5"	x 72"
.195"	x 16.5"	x 72"	.500"	x 16.5"	x 72"
.270"	x 16.5"	x 72"	.750"	x 16.5"	x 72"
.320"	x 16"	x 63"	1	x 16"	x 72"
.375"	x 16"	x 72"	2	x 4.25"	x 48"
.410"	x 16.5"	x 72"			Billet

Custom plate sizing available upon request.
We have shearing and saw cutting capabilities for plate.

42 Alloy Sheet

Thick.	Width	Length
.015"	x 12"	x 72"
.020"	x 24"	x 72"
.030"	x 24"	x 72"
.040"	x 24"	x 72"
.061"	x 24"	x 72"
.100"	x 24"	x 72"
.125"	x 24"	x 72"

We can shear to your width.

42 Alloy Roundbar

Diameter	Length
.125"	x 72"/144"
.156"	x 72"/144"
.1875"	x 144"
.255"	x 115"
.312"	x 115"
.437"	x 132"/144"
.750"	x 135"
1.01"	x 135"

Custom Wire sizes available upon request.

42 Alloy Coil

Base - Lead Frame - Deep Draw & Chemical Milling Quality

.004" x 12"	.0095" x 12"	.020" x 12"
.0045" x 1"	.010" x 12"	.025" x 12"
.005" x 12"	.010" x 12"	.030" x 12"
.006" x 12"	(halfhard)	.040" x 12.5"
.0075" x 12"	.0142" x 12"	.050" x 12" I
.008" x 12"	.015" x 12"	.060" x 12"

Custom sizes available upon request.
Slitting, Cut to Length and Traverse Winding services available.

Certified To AMS/MIL I 23011 Class 5 • All Above Available From Stock

NEA ISO 9001 Certified
Specialty Metal Service Center
Dedicated to Customer Service & Quality

NATIONAL ELECTRONIC ALLOYS
www.nealloys.com

EAST COAST

3 Fir Court, Oakland, NJ 07436
201-337-9400 • Fax: 201-337-9698
Toll Free: 800-524-4309
Email: Sales@nealloys.com

WEST COAST

1847 W. Business Center Dr., Orange, CA 92867
714-556-5561 • Fax: 714-556-5562
Toll Free: 877-632-9378
Email: Sales@nealloyswest.com